



Alu-Zinc Spray MG

Product description

Alu-Zinc Spray MG is a ready-to-use one-component product. It protects and restores protection against corrosion. Brilliant finishing.

Properties

- Good resistance against mechanical shocks, rubbing and erosion
- Very economic, effective and reliable
- Also suitable for spot welding
- Good electrical conductor
- Good weather resistance
- Can be used as finishing or it is overpaintable
- Provides a shiny finishing coat

Applications

- Alu-Zinc Spray MG has a galvanizing action. Protects zinc and unprocessed iron and steel against corrosion.
- To be used for coachwork, gutter braces and weld joints, also suitable for spot welding.
- Due to its cathode action, the spray is effective and reduces waste.
- Can also be use for tanks, slits, railings, gates, carpentry works,...



Technical data

Consistency	Liquid
Curing system	Physical drying
Curing speed	Cured and paintable after 24 hours
Drying time	Dust dry after 10 min, tack-free after 20 min
Application temperature	5°C → 35°C
Temperature resistance	-30°C → 120°C
Yield	1,5 → 2m ²
Flashpoint	<0°C
Solid content	18,5%
Volatile organic compounds (VOC)	54%

Substrates

- Substrate condition
The surface must be rigid, clean, dry, free of dust and grease.
- Substrate preparation
A preliminary adhesion test on every substrate is recommended. Remove rust.
- Substrate types
Metals



Alu-Zinc Spray MG

Application method

■ Application method

Apply on dry and grease-free surface, remove old loose paint and rust first. Shake can well before use. Apply on dry ground and dry conditions. Spray at a distance of appr. 20 cm of the object. Shake the canister thoroughly before applying each layer. Apply Alu-Zinc Spray MG always in 2 layers with an interval of min. 2 hours (repaintable after 24 hours with finishing coat).

Health- and Safety Recommendations

Use only in well-ventilated areas.

Dangerous. Respect the precautions for use.

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.

Packaging/Logistics

Colour: Alu silver

Shelf life: 3 years in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

Remarks

- After use, spray the aerosol can upside down for about 3 seconds to clean the valve until only propellant comes out. Thus avoiding the valve becomes blocked with zinc residues.

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.